



TECHNICAL DATA SHEET

CMC TYPE	10166
Supporting Base	polyester
Colour	colourless
Substrate thickness in mm	0.050 ± 10%
Total thickness in mm	0.080 ± 10%
Adhesive Properties	
Type of adhesive	acrylic
Adhesive strength in N/cm according to internal method PV 1006-32 (180° peel from steel)	≥ 3
Thermal Properties	
Temperature performance (max.) in °C	130
Short term temperature performance in °C (ca. 1 hour)	175
Flammability according to IEC 60454-2	flame retardant
Insulation class according to IEC 60454-2	B
Electrical Properties	
Voltage testing	no breakdown
Breakdown voltage on the basis of IEC 60243-1 in V _{eff.}	8'000
Electrolytic corrosion	AN 1,2
Mechanical Properties	
Tensile strength in N/10 mm	80
Elongation at break in %	80 - 120
Other Properties	
Liner	white siliconized paper

Storage conditions: cool and dry (15 - 25°C, < 65% rel. humidity)

11/13

Quality guarantee: 12 months

The technical data are average values and subject to change without notice. They are not intended to replace user's testing.