

**TECHNICAL DATA SHEET**

CMC TYPES	29030
Product description CMC 29030 is a non-coated, heat shrinkable polyester film for all applications requiring high thermal shrinkage.	
Film material	PET (polyethylene terephthalate)
Density	1.4 g/cm ³
Mechanical properties	
Tensile strength (machine direction)	about 200N/mm ²
Elongation at break (machine direction)	about 150%
Thermal properties	
Shrinkage (machine direction, 30 min 150°C)	ca. 24 – 35%
Shrinkage (cross machine direction, 30 min 150°C)	ca. 5 - 10%
Electrical properties	
Breakdown voltage based on IEC 60243-1	about 4.5KV
Other properties	

Storage conditions: cool and dry (15 - 25°C, < 65% rel. humidity)

10/15

Quality guarantee: 12 months

The technical data are average values and subject to change without notice. They are not intended to replace user's testing. All information transferred from the original data sheets of our suppliers (except electrical properties).