



TECHNICAL DATA SHEET

CMC TYPE Films of oxygen soft copper with tin coating on both sides		CMC 98035 CMC 98050 CMC 98070 CMC 98100	35 µm 50 µm 70 µm 100 µm
Core film			
DIN designation		E-Cu 58	
Copper content		≥ 99.9%	
Oxygen content		0.005 bis 0.04%	
Density		8.9 g/cm³	
Tin layer			
Designation		L-Sn 96.5 Ag 3.5	
Tin layer ratio		4% each side based on the total thickness	
Mechanical Properties			
			
These products as to their composition comply with the requirements of regulation 2011/65/EU (RoHS).			

All information transferred from the original data sheets of our suppliers.

03/16

Storage conditions: cool and dry (15 - 25°C, < 65% rel. humidity)

Quality guarantee: 12 months

The technical data are average values and subject to change without notice. They are not intended to replace user's testing.